

STAIN REMOVAL GUIDE:

Natural stone is porous by nature and will stain. Because stone is porous you can sometimes remove the stain by reversing the staining process. If you re-absorb the stain into a medium, you can remove it from the stone. The typical medium is called a poultice.

Stains should be treated as soon as possible. As time goes by it becomes increasingly difficult to remove the stain. Attempts to remove stains should not precede stain determination. Using the appropriate removal technique is important to achieve desired results. You must ask questions to determine what the stain is. What is the color? Where is it located? How long has it been there? Is it associated with the main traffic areas? Are plants near the stain? Etc..

Test patches will need to be performed. In many cases it will take several tests. Once the stain has been identified the following procedures can be followed.

POULTICING MATERIALS:

COTTON BALLS
PAPER TOWELS
FABRIC

POULTICING POWDERS:

MIRA SEAL POULTICE PLUS
CLAYS, FULLERS EARTH
DIATOMACEOUS EARTH

Poultice Plus powder, clays and diatomaceous earth are usually the best. Many stains are so deeply imbedded that a chemical solution will need to be added to the poultice to dilute and/or react with the stain. The process can be simple.

Mix **Poultice Plus** powder with distilled water or the chemical you have selected, to make a paste like substance. Apply the paste to the stain and do not let any excess drip or spill onto adjacent clean areas. The paste should have a consistency similar to peanut butter. The paste should be applied approximately 1/8 to 1/4 inch thick overlapping the stain by 1/2 to 1 inches. Cover the area with plastic wrap and secure the edges down with nonmarking tape. The poultice must dry completely. As the poultice dries it will pull the stain from the area into the paste. Drying time is usually 24-48 hours depending on the type of poultice being utilized. If the stain has improved, re-apply the poultice. Multiple applications may be required.

SPECIAL NOTES:

Some chemicals necessary for stain removal will remove the finish on polished marble, limestone, terrazzo and travertine. As a result, repolishing with abrasives or polishing compounds may be necessary.

TYPICAL STAINS:

| | |
|-------------|---|
| ORGANIC: | Coffee, tea, tobacco, food, cosmetics, plant, food. |
| INORGANIC: | Rust, iron, bronze, steel, metal. |
| BIOLOGICAL: | Mildew, mold, fungus and algae. |
| OIL BASE: | Grease, cooking oil, food stains, tar, body oil |
| INK: | Ball Point Pen or Magic Marker. |

STAIN REMOVAL GUIDE

ALWAYS TEST A SMALL AREA TO ENSURE THE DESIRED RESULTS

| CHALLENGE | SOLUTION | | | | | | | | | | | | |
|--------------------------------------|--|------------------------------|--|----------------------------------|--|------------------------------|----------------------------|---------------------------------|----------------------------|--------------------------------------|--------------------|------------------------|--|
| IRON STAINS: | Clean with one of the following: <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. Naval Jelly</td> <td style="width: 50%;">4. Oxalic Acid</td> </tr> <tr> <td>2. MiraSeal Liquid Poultrice</td> <td>5. GCFR (Grout Concrete Film Remover)</td> </tr> <tr> <td>3. Ammonium Oxalate</td> <td></td> </tr> </table> | 1. Naval Jelly | 4. Oxalic Acid | 2. MiraSeal Liquid Poultrice | 5. GCFR (Grout Concrete Film Remover) | 3. Ammonium Oxalate | | | | | | | |
| 1. Naval Jelly | 4. Oxalic Acid | | | | | | | | | | | | |
| 2. MiraSeal Liquid Poultrice | 5. GCFR (Grout Concrete Film Remover) | | | | | | | | | | | | |
| 3. Ammonium Oxalate | | | | | | | | | | | | | |
| INK STAINS: | Poultrice with one of the following: <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. MiraSeal Liquid Poultrice</td> <td style="width: 50%;">3. Light Colors: Bleach or Hydrogen Peroxide</td> </tr> <tr> <td>2. MiraSeal Mira Strip</td> <td>4. Dark Colors: Acetone or Lacquer Thinner</td> </tr> </table> | 1. MiraSeal Liquid Poultrice | 3. Light Colors: Bleach or Hydrogen Peroxide | 2. MiraSeal Mira Strip | 4. Dark Colors: Acetone or Lacquer Thinner | | | | | | | | |
| 1. MiraSeal Liquid Poultrice | 3. Light Colors: Bleach or Hydrogen Peroxide | | | | | | | | | | | | |
| 2. MiraSeal Mira Strip | 4. Dark Colors: Acetone or Lacquer Thinner | | | | | | | | | | | | |
| OIL BASE STAINS: | Clean with <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. MiraSeal Mira Clean #1</td> <td style="width: 50%;">5. Bleach</td> </tr> <tr> <td>2. MiraSeal Tile & Grout Cleaner</td> <td>6. Household Detergent</td> </tr> <tr> <td>3. MiraSeal Liquid Poultrice</td> <td>7. Ammonia</td> </tr> <tr> <td>4. MiraSeal Mira Strip</td> <td>8. Mineral Spirits</td> </tr> </table> Poultrice with one of the following: <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. Mineral Spirits</td> <td style="width: 50%;">3. Methyl Chloride</td> </tr> <tr> <td>2. MiraSeal Mira Strip</td> <td></td> </tr> </table> | 1. MiraSeal Mira Clean #1 | 5. Bleach | 2. MiraSeal Tile & Grout Cleaner | 6. Household Detergent | 3. MiraSeal Liquid Poultrice | 7. Ammonia | 4. MiraSeal Mira Strip | 8. Mineral Spirits | 1. Mineral Spirits | 3. Methyl Chloride | 2. MiraSeal Mira Strip | |
| 1. MiraSeal Mira Clean #1 | 5. Bleach | | | | | | | | | | | | |
| 2. MiraSeal Tile & Grout Cleaner | 6. Household Detergent | | | | | | | | | | | | |
| 3. MiraSeal Liquid Poultrice | 7. Ammonia | | | | | | | | | | | | |
| 4. MiraSeal Mira Strip | 8. Mineral Spirits | | | | | | | | | | | | |
| 1. Mineral Spirits | 3. Methyl Chloride | | | | | | | | | | | | |
| 2. MiraSeal Mira Strip | | | | | | | | | | | | | |
| ORGANIC STAINS: | Clean with: <ol style="list-style-type: none"> 1. MiraSeal Mira Clean #1 2. MiraSeal Tile & Grout Cleaner 3. MiraSeal Liquid Poultrice 4. 35% Hydrogen Peroxide. Pour directly on the stain and then add a few drops of ammonia. Leave until bubbling stop. Poultrice with same as above. | | | | | | | | | | | | |
| COPPER STAINS: | Poultrice with: <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. Ammonia Chloride</td> <td style="width: 50%;">2. Ammonia Hydroxide</td> </tr> </table> | 1. Ammonia Chloride | 2. Ammonia Hydroxide | | | | | | | | | | |
| 1. Ammonia Chloride | 2. Ammonia Hydroxide | | | | | | | | | | | | |
| BIOLOGICAL STAINS: | Clean with: <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. MiraSeal Mira Clean #1</td> <td style="width: 50%;">4. Diluted Ammonia</td> </tr> <tr> <td>2. MiraSeal Tile & Grout Cleaner</td> <td>5. Bleach</td> </tr> <tr> <td>3. MiraSeal Liquid Poultrice</td> <td></td> </tr> </table> | 1. MiraSeal Mira Clean #1 | 4. Diluted Ammonia | 2. MiraSeal Tile & Grout Cleaner | 5. Bleach | 3. MiraSeal Liquid Poultrice | | | | | | | |
| 1. MiraSeal Mira Clean #1 | 4. Diluted Ammonia | | | | | | | | | | | | |
| 2. MiraSeal Tile & Grout Cleaner | 5. Bleach | | | | | | | | | | | | |
| 3. MiraSeal Liquid Poultrice | | | | | | | | | | | | | |
| CRYSTALLIZATION COATINGS: | Rehone the Surface With Abrasives. | | | | | | | | | | | | |
| GROUT & THIN SET RESIDUE: | Cementitious: <p>Clean with</p> <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. MiraSeal GCFR</td> <td style="width: 50%;">Not recommended</td> </tr> <tr> <td>On Polished Surfaces:</td> <td>Dilute to a ratio of 5 - 1</td> </tr> <tr> <td>On Honed Surfaces:</td> <td>Dilute to a ratio of 5 - 1</td> </tr> <tr> <td>On Flamed or Textured Surfaces:</td> <td>Dilute to a ratio of 3 - 1</td> </tr> </table> Epoxy: <p>Clean with:</p> <table border="0" style="width: 100%;"> <tr> <td style="width: 50%;">1. MiraSeal Epoxy Grout Film Remover</td> <td style="width: 50%;">Use undiluted</td> </tr> <tr> <td>On All Surfaces:</td> <td></td> </tr> </table> | 1. MiraSeal GCFR | Not recommended | On Polished Surfaces: | Dilute to a ratio of 5 - 1 | On Honed Surfaces: | Dilute to a ratio of 5 - 1 | On Flamed or Textured Surfaces: | Dilute to a ratio of 3 - 1 | 1. MiraSeal Epoxy Grout Film Remover | Use undiluted | On All Surfaces: | |
| 1. MiraSeal GCFR | Not recommended | | | | | | | | | | | | |
| On Polished Surfaces: | Dilute to a ratio of 5 - 1 | | | | | | | | | | | | |
| On Honed Surfaces: | Dilute to a ratio of 5 - 1 | | | | | | | | | | | | |
| On Flamed or Textured Surfaces: | Dilute to a ratio of 3 - 1 | | | | | | | | | | | | |
| 1. MiraSeal Epoxy Grout Film Remover | Use undiluted | | | | | | | | | | | | |
| On All Surfaces: | | | | | | | | | | | | | |